REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden to Washington Headquarters Service, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188) Washington, DC 20503.

PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.

1. REPORT DATE (DD-MM-YYYY)

2. REPORT DATE

3. DATES COVERED (From - To)

- Dan to a De tte i tte i etti i etti etti				
1. REPORT DATE (DD-MM-YYYY) 08-00-2003	2. REPORT DATE Final Technical Report		3. DATES COVERED (From - To) July 00 - June 03	
4. TITLE AND SUBTITLE HETEROJUNGTION DEVICES BASED ON SILICON CARBIDE ALLOYED WITH GERMANIUM			TRACT NUMBER	
, LEG ES WITT GET WWW. WIGHT		5b. GRANT NUMBER N00014-00-1-0834		
		5c. PROGRAM ELEMENT NUMBER		
6. AUTHOR(S) James Kolodzey		5d. PROJECT NUMBER 03-3-21-3130-37		
		5e. TASI	K NUMBER	
		5f. WOR	K UNIT NUMBER	
7. PERFORMING ORGANIZATION NAM University of Delaware Electrical and Computer Enginee 140 Evans Hall Newark, DE 19716			8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENO Office of Naval Research Ballston Centre Tower One	CY NAME(S) AND ADDRESS(ES)		10. SPONSOR/MONITOR'S ACRONYM(S) ONR	
800 North Quincy Street Arlington, VA 22217-5660			11. SPONSORING/MONITORING AGENCY REPORT NUMBER	

12. DISTRIBUTION AVAILABILITY STATEMENT

Approved for Public Release; distribution is unlimited.

13. SUPPLEMENTARY NOTES

14. ABSTRACT

15. SUBJECT TERMS

We produced the alloy and found the Ge is substitutional with no defects, is stable up to 1600 C, and has promising device proprieties.

20041221 260

16. SECURITY	CLASSIFICATION	ON OF:	17. LIMITATION OF ABSTRACT	18. NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON
a. REPORT	b. ABSTRACT	c. THIS PAGE		. <u>.</u>	19b. TELEPONE NUMBER (Include area code)





Devices Based on Silicon Carbide Alloyed with Germanium

James Kolodzey
Electrical and Computer Engineering
University of Delaware
August 2003

A progress report to the Office of Naval Research: Dr. Harry Dietrich

Contract number: N0001-4-00-1-0834

Prof. James Kolodzey

Department of Electrical & Computer Eng.

140 Evans Hall

University of Delaware

Newark, DE 19716

tel: (302) 831-1164

fax: (302) 831-4316

email: kolodzey@ee.udel.edu

http://www.ee.udel.edu/~kolodzey





- James Kolodzey, University of Delaware
- Uniqueness: fabrication and characterization of new alloys of SiC and Ge
- Objective: investigate suitability of the alloys for SiC-based heterostructures.
- Progress & results: we produced the alloy and found the Ge is substitutional with no defects, is stable up to 1600 C, and has promising device proprieties
- MRS Fall Meeting 2002, Mat. Res. Soc. Symp. Proc. v. 742, References: J. Kolodzey et al., "Pseudomorphically Strained Layers in 4H-SiC formed by Germanium Implantation," 2002, pp. K6.7.1 - K6.7.6.




Devices Based on Silicon Carbide Alloyed with Germanium


- What applications of Navy interest will this impact?
- high speed, power, temperature SiC heterostructure devices and circuits for electric systems
- Do you anticipate transitions, and if so to what program?
- If successful, this project will provide an impact similar to that of the nitride WBG materials system, but with a mature substrate



Material Characterization of SiC:Ge (4% Ge), 2003








central area was masked from the implantation ions; while the dark area is where it (left) SiC:Ge photo for the as-implanted wafer of 4H-SiC. The white stripe in the received the Ge ion beams.

(right) Before the ion implantation, the Ge distribution was simulated using James Ziegler's SRIM software. The projected Ge ion distribution profile, as well as the ion implantation steps and doses for each step, is shown in this graph, for SiC sample NG4per03




Characteristics of npn bipolar transistor of 4H-SiC with 0.7 % Ge layer as the base region.





above: cross sectional etch profile of the transistor SiC-1



above: The current voltage characteristics show a forward common base current gain $\alpha=0.8$. This device is being optimized in this program.

Base (p)

Emitter (n)

ဓိ

1E19-

Concentration (cm3)

SIC-2 with 0.7% Ge

1E21


Depth (Ang.)

1000

1E17

above: simulation result of the ion implantation, showing the npn emitter (N-doped), base (Ge and Ga doped) and collector regions

Thermal stability of the implanted SiC:Ge (~0.35% Ge) was investigated by HRXRD and FTIR reflection measurements



(left) x-ray spectra of SiC:Ge samples (Ge=0.3%) as-implanted (A.I.), and after 10 minute anneals at 1250°C, 1450°C and 1650°C.

(right) Infrared reflectance, where the incident light is 80° with respect to c-axis, for as-implanted sample (dotted line), and the SiC:Ge layers annealed at 1250°C and 1450°C. The 4H-SiC substrate reflectance is also shown.

After annealing, the new 945cm⁻¹ mode observed after implantation disappears and the characteristic 4H vibration reappears. The inset shows a close-up of the evolution of the 838cm⁻¹ 4H-FTO mode with annealing.